



**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE



TEST REPORT
DENEY RAPORU

AB-0583-T

21027429

09-21

Customer name: BRBEN TEKSTİL SAN. VE TİC. A.Ş.
Address: 2. ORG. SANAYİ BÖLG. 83207 nl Cad. No:2/10 ŞEHİTKAMİL/
GAZİANTEP
Buyer name: -
Contact Person: ADEM ALTAN
Order No: -
Article No: BR3PLY-27
Name and identity of test item: Black non-woven medical mask.
The date of receipt of test item: 10.09.2021
Re-submitted/re-confirmation date: -
Date of test: 10.09.2021-20.09.2021
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not specified.
Number of pages of the report: 6

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.


The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Date
20.09.2021

Customer Representative
Tuğba AKTAŞ

Head of Testing Laboratory
Sevim A. RAZAKI
20.09.2021

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.



EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T

21027429

09-21

REQUIRED TESTS	RESULT	COMMENTS
MICROBIOLOGICAL TESTS		
Bacterial Filtration Efficiency-BFE	P	TYPE IIR
Microbial Cleanliness(Bioburden)	P	
PHYSICAL PROPERTIES		
Breathability(Differential Pressure)	P	
Splash Resistance	P	
P: Pass F: Fail R: Refer to retailer technologist. Tests results were evaluated according to EN 14683:2019+AC :2019 Tablo 1 limit values.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified.If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T

21027429

09-21

TEST RESULTS

BACTERIAL FILTRATION EFFICIENCY (BFE)

Test Metod: (Bacterial Filtration Efficiency Testing –BFE /Ref: EN 14683:2019+AC:2019 Medical Face Masks, Requirements and Test Methods)

A specimen of the mask material is clamped between an impactor and an aerosol chamber. An aerosol of *Staphylococcus aureus* is introduced into the aerosol chamber and drawn through the mask material and the impactor under vacuum. The bacterial filtration efficiency of the mask is given by the number of colony forming units passing through the medical face mask material expressed as a percentage of the number of colony forming units present in the challenge aerosol.

Test Flow Rate	28,3 L/min
Test Flow Time	2 minute
Sample Sizes	5 pieces mask
Microorganism	<i>Staphylococcus aureus</i> ATCC 6538
Bacterial concentration (cfu/ ml)	5x10 ⁵ cfu/ ml
incubation conditions	24 hour, 35°C ± 2°C
Positive control sample average of number of Bacteria (C)	3x10 ³ cfu/ ml

RESULTS			
Number of Test Sample	Test Sample (T) Number of Bacteria (cfu/ml)	Bacterial Filtration Efficiency (% B)	Requirement BFE (%)
1	35	%98,8	Type I ≥95 Type II ≥98
2	32	%98,9	
3	36	%98,7	
4	39	%98,8	
5	42	%98,7	

cfu: Colony-forming unit

$$B = (C - T) / C \times 100$$

%B: Bacterial Filtration Efficiency

C: is the mean of the total plate counts for the two positive control runs

T: is the total plate count for the test specimen

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T

21027429

09-21

TEST RESULTS

MICROBIAL CLEANLINESS (Bioburden)

Test Metod: EN ISO 11737-1:2018

The sample is put in extraciton liquid after shaking well, inoculated on the agar.

After incubation at 30 ± 1 ° C for 72 hours, growth microorganisms are counted on the agar.

	RESULTS	REQUIREMENT
Microbial cleanliness (cfu/g)	0 cfu/g	≤ 30 cfu/g Type I and Type II mask

*cfu= Colony forming unit.

BREATHABILITY (Differential Pressure)

Test Method: EN 14683:2019+AC :2019 (TS EN 14683+AC:2019) Annex-C

Test Condition (21 ± 5) °C ve (85 ± 5) % relative humidity, 4 hrs

Test area is 25 mm in diameter , 5 different sample was taken

Adjusted airflow is 8 l/min. The differential pressure is read directly using a differential pressure manometer .

SAMPLE	DIFFERENTIAL PRESSURE RESULT	REQUIREMENT
1	36,2 Pa/cm ²	< 60 Pa/cm²
2	35,8 Pa/cm ²	
3	39,1 Pa/cm ²	
4	37,1 Pa/cm ²	
5	36,0 Pa/cm ²	
Average Result	36,8 Pa/cm ²	

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T

21027429

09-21

TEST RESULTS

SPLASH RESİSTANCE (ONLY FOR TYPE IIR)

Test Metod: EN 14683:2019+AC :2019 (Clause 5.2.4) the resistance of the medical face mask to penetration of splashes of liquid shall conform to the minimum value given for Type IIR in Table 1

ISO 22609 :2004 Clothing for protection against infectious agents — Medical face masks — Test method for resistance against penetration by synthetic blood (fixed volume, horizontally projected)

Test Condition (21 ± 5) °C ve (85 ± 5) % relative humidity, 4 hrs

32 different samples were taken

	<u>SPLASH RESISTANCE PRESSURE (kPa)</u>	<u>RESULTS</u>	<u>REQUIREMENT</u>
1	>21.3 kPa	PASS	≥16 kPa
2	>21.3 kPa	PASS	
3	>21.3 kPa	PASS	
4	>21.3 kPa	PASS	
5	>21.3 kPa	PASS	
6	>21.3 kPa	PASS	
7	>21.3 kPa	PASS	
8	>21.3 kPa	PASS	
9	>21.3 kPa	PASS	
10	>21.3 kPa	PASS	
11	>21.3 kPa	PASS	
12	>21.3 kPa	PASS	
13	>21.3 kPa	PASS	
14	>21.3 kPa	PASS	
15	>21.3 kPa	PASS	
16	>21.3 kPa	PASS	
17	>21.3 kPa	PASS	
18	>21.3 kPa	PASS	
19	>21.3 kPa	PASS	
20	>21.3 kPa	PASS	
21	>21.3 kPa	PASS	
22	>21.3 kPa	PASS	
23	>21.3 kPa	PASS	
24	>21.3 kPa	PASS	
25	>21.3 kPa	PASS	
26	>21.3 kPa	PASS	

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T

21027429

09-21

27	>21.3 kPa	PASS	
28	>21.3 kPa	PASS	
29	>21.3 kPa	PASS	
30	>21.3 kPa	PASS	
31	>21.3 kPa	PASS	
32	>21.3 kPa	PASS	
Average Result	>21.3 kPa	PASS	